



Automotive Window Film Performance Specifications

	Total Solar Energy:			Visible Light:		"U" Factor:		UV Rejection	Shading Coefficient	Solar Heat Gain Coefficient	Glare Reduction	Total Solar Energy Rejected
	Transmitted	Reflected	Absorbed	Transmitted	Reflected	Median	Design					
Shadow Series												
Shadow 5 - PS SR	49%	6%	45%	6%	5%	1.04	1.05	99%	0.73	0.64	93%	36%
Shadow 20 - PS SR	57%	6%	37%	23%	5%	1.04	1.05	99%	0.78	0.68	75%	32%
Shadow 32 - PS SR	59%	7%	34%	31%	5%	1.03	1.04	99%	0.8	0.70	66%	30%
Shadow 38 - PS SR	64%	6%	30%	42%	5%	1.04	1.05	99%	0.84	0.73	53%	27%
Shadow 50 - PS SR	66%	7%	27%	50%	6%	1.03	1.04	99%	0.85	0.74	45%	26%
GP Max Series												
GP Max 5	18%	22%	60%	5%	8%	0.98	1.00	99%	0.41	0.36	95%	64%
GP Max 20	40%	9%	51%	20%	5%	1.02	1.03	99%	0.64	0.56	77%	44%
GP Max 35	47%	10%	44%	40%	8%	1.01	1.03	99%	0.69	0.60	55%	40%
GP Max 50	68%	7%	25%	47%	6%	1.08	1.13	99%	0.87	0.76	47%	24%

Specification Use Statement

Reported values are typical properties and should not be used as a specification. Since the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for intended use. If you need verification regarding specific use or additional information, please contact Madico Window Films or your local Madico Authorized Dealer.